



SUSTAINABLE DYEING

- 1

Wetting at 70 C for 10 min
- 2

Cationization at 75 C for 30 min
- 3

Earth Dyeing at 70 C for 40 min
- Drain
- Rinse
- 4

Binder at 40 C for 10 min
- Rinse
- 5

Bio Polish at 55 C for 25 min ph 4.5
- 6

Hydroextraction
- 7

Drying at 75 C for 40 min