RCJC

GARMENT DYEING WITH PP STROKE

1 Wetting at 70°
for 10 Minutes

2 Dyeing at 60° for
40 Minutes

Check Sample

If Ok

Not Ok

Do
Addition

Again run for 20 Mins
Then check Sample

Drain

Rinse

3 Neutral at 40 C
for 10 Minutes

4 Rinse x2
Soaping at 70C
for 15 Minutes

5 Rinse
Bio Polish at 55 C
for 25 min ph 4.5

6 Rinse
Softening at 40 C
for 20 min

7 Hydroextraction

8 Drying

9 PP Stroke

10 Neutralisation

11 Fixing with Fixer

12 Softening at 40 C
for 20 min

13 Hydroextraction

14 Drying at 75 C
for 45 min